# Moravia

## **TECHNICAL DATA SHEET**

TDS 022 / 01 Document No / Rev. Date 12.08.2024 Page No 1/2



# Morabilge

# **Product Description**

Morabilge is a glossy topcoat paint designed for bilges. Good weather and colour stability.

#### Intended Uses

It is used to protect bilges from abrasion and its resistance to chemicals is excellent.

**Physical Properties** 

**Physical State** : Liquid Colour : White, grey Volume Solid (%) : 45 ± 3

**Density**  $: 1,15 \pm 0,05 \text{ kg/L}$ 

Gloss : Glossy **Flexibility** : Good

**Application Data** 

Mixing Ratio (volume) : Single component **Application Methods** : Brush, roller or spray

**Application Conditions** : The temperature of the substrate should be minimum 3°C above the

dew point of the air. Good ventilation is required.

Wet (µm)

Theoretical Coverage (m<sup>2</sup>/L)

Thinner/Cleaner : Moravia 009 Thinner

**Guiding data for airless spray** 

Pressure at nozzle : 15 MPa (150 kp/cm<sup>2</sup> 2100 psi) : 0.33-0.43 mm (0.013-0.017") Nozzle tip

: 40-80° Spray angle

Filter : Check to ensure that filters are clean.

Dry (µm)

Typical film thickness

40 89 11,25 **Maximum thickness** 50 111 9.00

# Moravia

### **TECHNICAL DATA SHEET**

Document No / Rev. TDS 022 / 01
Date 12.08.2024
Page No 2 / 2

#### **Surface Preparations**

All surfaces to be coated should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

#### Steel surface

Blast-cleaning to Sa 2½ (ISO-8501). Power tool cleaning to min. St 2 (ISO 8501) may be acceptable, subject to exposure conditions. After this process, the appropriate primers are used and this paint can be applied as a top coat respectively.

#### Coated surface

Use compatible primer for alkyd paint system. Please contact Moravia office for further information.

#### **Drying Time**

Substrate Temperature	Touch Dry	Hard Dry	Over coating Data	
			Minimum	Maximum
10°C	8 hrs	40 hrs	40 hrs	
23°C	3 hrs	24 hrs	16 hrs	-
35°C	2 hrs	12 hrs	12 hrs	

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

**Packing Size** : 0,75 L, 2,5 L, 20 kg

#### Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated area and away from source of heat and ignition. Containers must be kept tightly closed.

# **Health and Safety**

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

**Disclaimer:** The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.