

Moravia	TEKNİK BİLGİ FORMU	Doküman No / Rev. TBF 013 / 02 Tarih 07.07.2023 Sayfa No 1 / 2
----------------	---------------------------	--



Moravia
Marine Coatings

Moracrylic

Product Description

Moracrylic is a two-component, acrylic polyurethane based high gloss topcoat with aliphatic isocyanate curing. It has perfect colour and gloss retention. Resistance to humidity, UV and chemicals is excellent.

Intended Uses

With suitable primer, it can be used for a long time for every surface in very hard atmosphere conditions.

Physical Properties

Physical State	: Liquid
Colour	: Moravia catalogue
Volume Solid (%)	: 51 ± 3
Density	: 1,22 ±0,05 kg/L
Gloss	: Glossy
Flexibility	: Flexible

Application Data

Mixing Ratio (weight)	: 4 units Part A / 1 unit Part B
Mixing Ratio (volume)	: 3 units Part A / 1 unit Part B
Application Methods	: Airless spray, conventional spray, brush and roller.
Application Conditions	: The temperature of the substrate should be minimum 3°C above the dew point of the air. Good ventilation is required.
Thinner/Cleaner	: Moravia 012 Thinner

Guiding data for airless spray

Pressure at nozzle	: 15 MPa (150 kp/cm ² 2100 psi)
Nozzle tip	: 0.28-0.38 mm (0.011-0.015")
Spray angle	: 40-80°
Filter	: Check to ensure that filters are clean.

	Dry (µm)	Wet (µm)	Theoretical Coverage (m²/L)
Typical film thickness	50	98	10,20
Maximum thickness	60	117	8,50

Moravia	TEKNİK BİLGİ FORMU	Doküman No / Rev. TBF 013 / 02 Tarih 07.07.2023 Sayfa No 2 / 2
----------------	---------------------------	--

Surface Preparations

All surfaces to be coated should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Steel surface

Blast-cleaning to Sa 2½ (ISO-8501). Power tool cleaning to min. St 2 (ISO 8501) may be acceptable, subject to exposure conditions.

Coated surface

Clean, dry and scatheless suitable lining. Please contact Moravia office for further information.

Drying Time

Substrate Temperature	Pot Life (max)	Touch Dry	Hard Dry	Over coating Data	
				Minimum	Maximum
10°C	18 hours	3,5 hours	12 hours	16 hours	-
23°C	8 hours	2,5 hours	6 hours	8 hours	-
30°C	3 hours	1 hour	4,5 hours	5 hours	-

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Packing Size : 20 kg

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated area and away from source of heat and ignition. Containers must be kept tightly closed.

Health and Safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

Disclaimer: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.